



# MATERIAL SPECIFICATION SHEET

## GRADE: 17B2



### Material nº:

No: **1.5502**

### Equivalencia norma - Standard Reference:

DIN EN 10263-4

### Tipo de acero - Steel type:

Case hardening steels

### Aplicación - Application:

Wire rod for a process of cold heading / cold extrusion, with a high productivity using punch and dies to transform a steel wire rod at room temperature.

Boron Steels are killed with Aluminium and Titanium, which allow enough Boron to be active in order to guarantee the quenching hardenability of the steel

### Composición química (%) - Chemical composition (%):

Element	Min	Max
%C	0,15	0,20
%Mn	1,00	0,90
%Si		0,025
%P		0,025
%S		0,30

Element	Min	Max
%Cr		0,30
%Ni		0,15
%Cu		0,25
%B		0,0050
%Al		0,060
%N		0,0100

### ***Característica mecánicas bruto - Mechanical characteristics (As rolled)***

---

**Resistencia** - Tensile strength (Mpa) 580 max

**Estricción** – Reduction of Area (%) 65 min

### ***Característica mecánicas recocido globular - Mechanical characteristics (As annealed)***

---

**Resistencia** - Tensile strength (Mpa) 500 max

**Estricción** – Reduction of Area (%) 65 min

### ***Tolerancias dimensionales - Dimensional tolerances***

---

According to **EN 10108 Class B**

### ***Calidad superficial - Surface quality***

Característica mecánicas recocido globular - Mechanical characteristics (As annealed)

According to **ISO 9443:2018 class B**

Material verified by **Eddy Current Control**

## Dimensiones y peso del rollo – Coil dimensions and coil weight



**3100 kg or 2600 kg aprox.** and half coils packed together of 1650 kg or 1300 kg aprox.  
Each coil tied minimum with four strips

### Stelmor line (rod sizes from 5.5 up to 24.0 mm)

Coil weight (kg) aprox.	Coil length (mm) aprox.	Inner diameter (mm) aprox.	Outer diameter (mm) aprox.
2600	1800	800	1250
3100	2000	800	1250

Note: when cutting the coil ties, the length can be increased significantly.

### Stelmor line: Half coils

Coil weight (kg) aprox.	Coil length (mm) aprox.	Inner diameter (mm) aprox.	Outer diameter (mm) aprox.
1300	900	800	1250
1550	1000	800	1250

Note: half coils are delivered in bundles of two coils packed together

### Hot coiling line (rod sizes from 25.0 up to 52.0 mm)

Coil weight (kg) aprox.	Coil length (mm) aprox.	Inner diameter (mm) aprox.	Outer diameter (mm) aprox.
2600	1700	880	1300
3100	1800	880	1300

Note: when cutting the coil ties, the length should not have a significant increase.  
Other coil weights could be made, if customer need