



MATERIAL SPECIFICATION SHEET

GRADE: C82+CR



Material nº:

No: -

Equivalencia norma - Standard Reference:

ASTM A29/A29M

Other references:

-

Tipo de acero - Steel type:

High strength wire rod

Aplicación - Application:

This designation includes wire rods with a very high content of carbon (0,75,0,88%), in some cases microalloyed with chrome and/or vanadium. The most common applications are wires and strands for pre and post-stressed concrete and high strength ropes.

Composición química (%) - Chemical composition (%):

| Element | Min | Max |
|---------|------|-------|
| %C | 0,78 | 0,84 |
| %Mn | 0,60 | 1,80 |
| %Si | 0,15 | 0,30 |
| %P | | 0,020 |
| %S | | 0,020 |
| %Cr | 0,20 | 0,30 |

Característica mecánicas bruto - Mechanical characteristics (As rolled)

Resistencia - Tensile strength (Mpa) 1150 min (depends on % Cr and % V) TS will be oscillate

Tolerancias dimensionales - Dimensional tolerances


According to **EN 10108 Class B**

Calidad superficial - Surface quality

According to **ISO 9443:2018 class B**

Material verified by **Eddy Current Control**

Dimensiones y peso del rollo – Coil dimensions and coil weight



3100 kg or 2600 kg aprox. and half coils packed together of 1650 kg or 1300 kg aprox.
Each coil tied minimum with four strips

Stelmor line (rod sizes from 5.5 up to 24.0 mm)

| Coil weight (kg) aprox. | Coil length (mm) aprox. | Inner diameter (mm) aprox. | Outer diameter (mm) aprox. |
|-------------------------|-------------------------|----------------------------|----------------------------|
| 2600 | 1800 | 800 | 1250 |
| 3100 | 2000 | 800 | 1250 |

Note: when cutting the coil ties, the length can be increased significantly.

Stelmor line: Half coils

| Coil weight (kg) aprox. | Coil length (mm) aprox. | Inner diameter (mm) aprox. | Outer diameter (mm) aprox. |
|-------------------------|-------------------------|----------------------------|----------------------------|
| 1300 | 900 | 800 | 1250 |
| 1550 | 1000 | 800 | 1250 |

Note: half coils are delivered in bundles of two coils packed together.

Hot coiling line (rod sizes from 25.0 up to 52.0 mm)

| Coil weight (kg) aprox. | Coil length (mm) aprox. | Inner diameter (mm) aprox. | Outer diameter (mm) aprox. |
|-------------------------|-------------------------|----------------------------|----------------------------|
| 2600 | 1700 | 880 | 1300 |
| 3100 | 1800 | 880 | 1300 |

Note: when cutting the coil ties, the length should not have a significant increase.
Other coil weights could be made, if customer needs.